PROSAT[®] Meltblown Polypropylene Wipes

Presaturated with 91% IPA and 9% DI water

Manufactured from meltblown polypropylene these PROSAT[®] presaturated wipes offer exceptional cleanliness. They are low in nonvolatile residues as well as particles and fibers. The use of presaturated wipes provides maximum process control.

Saturated with a blend of 91% isopropyl alcohol and 9% deionized water these wipes are an excellent choice for general surface cleaning where fast drying times are desired. The use of presaturated wipes reduces VOC emissions and solvent use up to 35% over spraying. The wipes are provided in convenient and easy to use peel and reseal pouches.



Features	Benefits
Presaturated with 91% isopropyl alcohol and 9% deionized water	• Excellent choice when fast drying times are required
Low in nonvolatile residue as well as particles and fibers	Ideal for multiple applications
Resealable pouch	Preserves cleanliness and solvent saturation levels

Part No.	Description	Size	Packaging
PS-919	PROSAT Meltblown Polypropylene Wipes,	9" x 11"	30/pouch;
	Presaturated with 91% IPA 9% DI Water	(230 x 280 mm)	50 pouches/case

PDSW042 | 090622

Copyright © 2022 Contec, Inc. All rights reserved.

Contact us: info@contecinc.com contecinc.com Contec, Inc. Spartanburg, SC 29303 USA tel: +1-864-503-8333



Product Inf	ormatio
-------------	---------

Technical Data Attribute (units)

Specific ions

Basis weight, nominal; (g/m²)

In deionized water; (g/m²)

In isopropyl alcohol; (g/m²)

Sodium; (ppm)

Chloride; (ppm)

Non-volatile residue, NVR

Particles, readily releasable

Particles $\geq 0.5 \mu m$; (x10⁶/m²)

Fibers > 100µm; (x 10³/m²)

Material	• 100% polypropylene	
Construction	Meltblown nonwoven	
Packaging materials	 Outer bags (OB1), low density polyethylene (LDPE) Case (CS), corrugated fiberboard (PAP) 	
Environment	ISO 5-8 Grade C/D	

Typical Value

36

0.011

0.070

3.0

5.0

19.7

6.3

Test Method

Contec Method

IEST-RP-CC004.3, Sec. 6.1.2

IEST-RP-CC004.3, Sec. 6.2.2

IEST-RP-CC004.2, Sec. 5.1

IEST-RP-CC004.2, Sec. 5.2

Recycle Symbols PET 1 HDPE 2 LDPE 4 PP 5 PAP 2

Packaging	EA/PCH	PCH/OB1	OB1/CS	EA/CS
PS-919	30	10	5	1,500

EA = each; OB = outer bag; PCH = pouch; CS = case; LBS = pounds

VOC Content	VOC (LBS/CS)	VOC (LBS/PCH)
PS-919	21.23	0.42

Notes

a) The data shown are typical values and should not be used as product specifications.

b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.

c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

d) All of Contec's packaging is compatible with hydrogen peroxide gassing applications.

e) These wipes are free of lint and loose fibers, and meet the definition of lint-free/low linting wipes according to the United States Pharmacopoeia Chapter 797 (USP-NF General Chapter

<797> Pharmaceutical Compounding -Sterile Preparations) and the Institute of Environmental Sciences and Technology Recommended Practice IEST-RP-CC004.4

1. CTM = Contec Test Method

2. IEST-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of environmental Sciences and Technology, Rolling Meadows IL.

PDSW042 | 090622

Copyright © 2022 Contec, Inc. All rights reserved.

Contact us: info@contecinc.com contecinc.com Contec, Inc. Spartanburg, SC 29303 USA tel: +1-864-503-8333



Test Methods: