PROSAT® Meltblown Polypropylene Wipes

Presaturated with 91% IPA and 9% DI water

Manufactured from meltblown polypropylene these PROSAT® presaturated wipes offer exceptional cleanliness. They are low in nonvolatile residues as well as particles and fibers. The use of presaturated wipes provides maximum process control.

Saturated with a blend of 91% isopropyl alcohol and 9% deionized water these wipes are an excellent choice for general surface cleaning where fast drying times are desired. The use of presaturated wipes reduces VOC emissions and solvent use up to 35% over spraying. The wipes are provided in convenient and easy to use peel and reseal pouches.

These wipes meet the requirements of USP<797> and IEST-CC-RP004.4 for "non-shedding, low-lint, lint-free wipes".



Features	Benefits	
Presaturated with 91% isopropyl alcohol and 9% deionized water	Excellent choice when fast drying times are required	
Low in nonvolatile residue as well as particles and fibers	Ideal for multiple applications	
Resealable pouch	Preserves cleanliness and solvent saturation levels	

Part No.	Description	Size	Packaging
PS-919	PROSAT Meltblown Polypropylene Wipes,	9" x 11"	30/pouch;
	Presaturated with 91% IPA 9% DI Water	(230 x 280 mm)	50 pouches/case


PDSW042 | 052025

Copyright © 2025 Contec, Inc. All rights reserved.



Product Information		
Material	100% polypropylene	
Construction	Meltblown nonwoven	
Packaging materials	Outer bags (OB1), low density polyethylene (LDPE) Case (CS), corrugated fiberboard (PAP)	
Environment	ISO 5-8 Grade C/D	

'					
Technical Data					
Attribute (units)	Typical Value	Test Method			
Basis weight, nominal; (g/m²)	36	Contec Method			
Non-volatile residue, NVR		IEST-RP-CC004.3, Sec. 6.1.2			
In deionized water; (g/m²)	0.011				
In isopropyl alcohol; (g/m²)	0.070				
Specific ions		IEST-RP-CC004.3, Sec. 6.2.2			
Sodium; (ppm)	3.0				
Chloride; (ppm)	5.0				
Particles, readily releasable		IEST-RP-CC004.2, Sec. 5.1			
Particles ≥ 0.5μm; (x10 ⁶ /m ²)	19.7				
Fibers ≥ 100µm; (x 10³/m²)	6.3	IEST-RP-CC004.2, Sec. 5.2			



EA = each; OB = outer bag; PCH = pouch; CS = case; LBS = pounds

VOC Content	VOC (LBS/CS)	VOC (LBS/PCH)
PS-919	21.23	0.42

Notes

- a) The data shown are typical values and should not be used as product specifications.
- b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.
- d) All of Contec's packaging is compatible with hydrogen peroxide gassing applications.
- e) These wipes are free of lint and loose fibers, and meet the definition of lint-free/low linting wipes according to the United States Pharmacopoeia Chapter 797 (USP-NF General Chapter <797> Pharmaceutical Compounding -Sterile Preparations) and the Institute of Environmental Sciences and Technology Recommended Practice IEST-RP-CC004.4

Test Methods:

- 1. CTM = Contec Test Method
- 2. IEST-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of Environmental Sciences and Technology, Rolling Meadows IL.

PDSW042 | 052025 Contec, Inc. All rights reserved.























