Product Data Sheet SATWIPES® Delta™ Wipes

SATWIPES® Delta[™] Wipes

100% Nonwoven polyester wipes presaturated with IPA/DI water

SATWIPES® Delta™ consists of a perforated roll of saturated wipes which are dispensed through a center-pull canister. The wipes consist of 100% nonwoven polyester fabric creating a soft, durable, and clean wipe. The isopropyl alcohol solvent blends provide safe cleaning solutions in various concentrations. Packaged with refill packs and a reusable pop-up dispenser, eliminating the need for solvent bottles and reduces solvent handling.



| Features | Benefits | |
|--------------------|---|--|
| Presaturated wipe | Eliminates the need for solvent bottles | |
| Reusable dispenser | Reduces solvent handling | |

| Part No. | Description | Size | Packaging |
|----------------|--|----------------|--------------------------|
| SAT-C3-100 | SATWIPES Delta Wipes, | 6" x 9" | 100/roll; |
| | Presaturated with 99% IPA | (152 x 230 mm) | 12 rolls + canister/case |
| SAT-C3-7030 | SATWIPES Delta Wipes, | 6" x 9" | 100/roll; |
| | Presaturated with 70% IPA/30% DI water | (152 x 230 mm) | 12 rolls + canister/case |
| SAT-C3-7030/18 | SATWIPES Delta Wipes, | 6" x 9" | 100/roll; |
| | Presaturated with 70% IPA/30% DI water | (152 x 230 mm) | 18 rolls |
| SAT-C3-694 | SATWIPES Delta Wipes, | 6" x 9" | 100/roll; |
| | Presaturated with 6% IPA/94% DI water | (152 x 230 mm) | 12 rolls + canister/case |
| SWC30064 | SATWIPES Delta Wipes, | 4.25" x 4" | 185/roll; |
| | Presaturated with 99% IPA | (108 x 102 mm) | 12 rolls + canister/case |
| SWC30140 | SATWIPES Delta Wipes, | 5.8" x 6" | 150/roll; |
| | Presaturated with 99% IPA | (147 x 152 mm) | 12 rolls + canister/case |
| SAT-C3-AC | SATWIPES Delta Wipes, | 6" x 9" | 100/roll; |
| | Presaturated with 100% acetone | (152 x 230 mm) | 12 rolls + canister/case |

PDSW051 | 101122

Copyright © 2022 Contec, Inc. All rights reserved.



Product Data Sheet SATWIPES® Delta™ Wipes

| Product Information | | |
|---------------------|--|--|
| Material | • 100% polyester | |
| Construction | Hydroentangled nonwoven | |
| Packaging materials | Case (CS), corrugated fiberboard (PAP) | |



| Technical Data | | | | | |
|--|---------------|-----------------------------|--|--|--|
| Attribute (units) | Typical Value | Test Method | | | |
| Basis weight, nominal; (g/m²) | 69 | Contec Method | | | |
| Non-volatile residue, NVR | | IEST-RP-CC004.2, Sec. 6.1.2 | | | |
| In deionized water; (g/m²) | 0.055 | | | | |
| In isopropyl alcohol; (g/m²) | 0.008 | | | | |
| Specific ions | | IEST-RP-CC004.2, Sec. 6.2.2 | | | |
| Sodium; (ppm) | 1.9 | | | | |
| Chloride; (ppm) | 4.7 | | | | |
| Particles, readily releasable | | IEST-RP-CC004.2, Sec. 5.1 | | | |
| Particles ≥ 0.5μm; (x10 ⁶ /m ²) | 16.5 | | | | |
| Fibers ≥ 100µm; (x 10³/m²) | 1.0 | IEST-RP-CC004.2, Sec. 5.2 | | | |

| Recycle Symbols | | | |
|-----------------|-----------|--|--|
| PET | A | | |
| HDPE | 2 | | |
| LDPE | 4 | | |
| PP | 15 | | |
| PAP | 201 | | |
| | | | |

| Packaging | EA/RL | RL/PCH | PCH/CS | EA/CS |
|----------------|-------|--------|--------|-------|
| SAT-C3-100 | 100 | 1 | 12 | 1,200 |
| SAT-C3-694 | 100 | 1 | 12 | 1,200 |
| SAT-C3-7030 | 100 | 1 | 12 | 1,200 |
| SAT-C3-7030/18 | 100 | 1 | 18 | 1,800 |
| SWC30064 | 185 | 1 | 12 | 2,200 |
| SWC30140 | 150 | 1 | 12 | 1,800 |
| SAT-C3-AC | 100 | 1 | 12 | 1,200 |

EA = each; PCH = pouch; RL = roll; CS = case

Notes

- a) The data shown are typical values and should not be used as product specifications.
- b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.
- d) All of Contec's packaging is compatible with hydrogen peroxide gassing applications.
- e) These wipes are free of lint and loose fibers, and meet the definition of lint-free/low linting wipes according to the United States Pharmacopoeia Chapter 797 (USP-NF General Chapter <797> Pharmaceutical Compounding -Sterile Preparations) and the Institute of Environmental Sciences and Technology Recommended Practice IEST-RP-CC004.4

 Test Methods:
- 1. CTM = Contec Test Method
- 2. IEST-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of environmental Sciences and Technology, Rolling Meadows IL

PDSW051 | 101122 Copyright © 2022 Contec, Inc. All rights reserved.