## **Polynit Wipes**

## 100% no-run interlock knit polyester wipe with knife cut edges

Polynit Wipes are made of 100% knitted textured polyester with knife cut edges for a very soft wipe. The soft edge is ideal for use on surfaces which are vulnerable to scratching. Polyester wipes are chemically resistant and exceptionally low in particles and fibers. An interlock knit creates a durable fabric, the addition of a periodic additional stitch of a no-run interlock knit prevents the fabric unraveling creating an even more durable fabric with strong edges.

The wipes are laundered and packaged in a cleanroom. They have good sorbency with solvents and are abrasion and chemical resistant.

A validated sterile version is available.



| Features                                | Benefits   |
|---|--|
| Laundered knitted 100% polyester fabric | • Extremely low levels of particles and fibers               |
| Soft edge                               | Ideal for use on surfaces which are vulnerable to scratching |
| 100% knitted polyester                  | Makes it compatible with many solvents                       |

PDSW075 | 101122

Copyright © 2022 Contec, Inc. All rights reserved.

Contact us: info@contecinc.com contecinc.com Contec, Inc. Spartanburg, SC 29303 USA tel: +1-864-503-8333



| Part No.   | Description    | Size           | Packaging    |
|------------|----------------|----------------|--------------|
| PN-44      | Polynit Wipes, | 4" x 4"        | 300/bag;     |
|            | Flat stacked   | (102 x 102 mm) | 16 bags/case |
| PN-44B     | Polynit Wipes, | 4" x 4"        | 600/bag;     |
|            | Bulk           | (102 x 102 mm) | 8 bags/case  |
| PN-99      | Polynit Wipes, | 9" x 9"        | 75/bag;      |
|            | Flat stacked   | (230 x 230 mm) | 16 bags/case |
| PN-99 B    | Polynit Wipes, | 9" x 9"        | 300/bag;     |
|            | Bulk           | (230 x 230 mm) | 4 bags/case  |
| PN-99B/150 | Polynit Wipes, | 9" x 9"        | 150/bag;     |
|            | Bulk           | (230 x 230 mm) | 8 bags/case  |
| PN-1212    | Polynit Wipes, | 12" x 12"      | 75/bag;      |
|            | Flat stacked   | (305 x 305 mm) | 10 bags/case |
| PN-1212B   | Polynit Wipes, | 12" x 12"      | 150/bag;     |
|            | Bulk           | (305 x 305 mm) | 4 bags/case  |

| Product Information |   |  |  |
|---------------------|---|--|--|
| Material            | • 100% polyester  |  |  |
| Construction        | • Interlock knit  |  |  |
| Packaging materials | <ul> <li>Outer bags (OB1, OB2), low density polyethylene (LDPE)<br/>Case (CS), corrugated fiberboard (PAP)</li> </ul> |  |  |
| Environment         | • ISO 3-8 Grade C/D   |  |  |



## Recycle Symbols



PDSW075 | 101122

Copyright  $\ensuremath{\mathbb{C}}$  2022 Contec, Inc. All rights reserved.

Contact us: info@contecinc.com contecinc.com Contec, Inc. Spartanburg, SC 29303 USA tel: +1-864-503-8333



| Technical Data   |                                 |                                  |                             |  |  |  |
|--|---------------------------------|----------------------------------|-----------------------------|--|--|--|
|  | PN-99B, PN-99B/150,<br>PN-1212B | PN-44, PN-44B,<br>PN-99, PN-1212 |                             |  |  |  |
| Attribute (units)  | Typical Value                   | Typical Value                    | Test Method                 |  |  |  |
| Basis weight, nominal; (g/m²)                                    | 140                             | 140                              | Contec Method               |  |  |  |
| Sorbent capacity; (mL/m²)  | 369                             | 357                              | IEST-RP-CC004.3, Sec. 8.1   |  |  |  |
| Sorptive rate; (seconds)   | <1                              | <1                               |                             |  |  |  |
| Non-volatile residue, NVR  |                                 |                                  | IEST-RP-CC004.3, Sec. 7.1.2 |  |  |  |
| In deionized water; (g/m²)                                       | 0.007                           | 0.003                            |                             |  |  |  |
| In isopropyl alcohol; (g/m²)                                     | 0.011                           | 0.018                            |                             |  |  |  |
| Specific ions  |                                 |                                  | IEST-RP-CC004.3, Sec. 7.2.2 |  |  |  |
| Sodium; (ppm)  | 0.157                           | 0.119                            |                             |  |  |  |
| Chloride; (ppm)  | 0.126                           | 0.042                            |                             |  |  |  |
| Particles, readily releasable                                    |                                 |                                  | IEST-RP-CC004.2, Sec. 5.1   |  |  |  |
| Particles <u>&gt;</u> 0.5µm; (x10 <sup>6</sup> /m <sup>2</sup> ) | 1.52                            | 6.9                              |                             |  |  |  |
| Fibers <u>&gt;</u> 100µm; (x 10³/m²)                             | 0.766                           | 0.53                             |                             |  |  |  |

| Packaging  | EA/OB1 | OB1/OB2 | OB2/CS | EA/CS |
|------------|--------|---------|--------|-------|
| PN-44      | 300    | 1       | 16     | 4,800 |
| PN-44B     | 600    | 1       | 8      | 4,800 |
| PN-99      | 75     | 2       | 8      | 1,200 |
| PN-99B     | 300    | 1       | 4      | 1,200 |
| PN-99B/150 | 150    | 1       | 8      | 1,200 |
| PN-1212    | 75     | 1       | 10     | 750   |
| PN-1212B   | 150    | 1       | 4      | 600   |
|            |        |         |        |       |

EA = each; OB = outer bag; CS = case

Notes

a) The data shown are typical values and should not be used as product specifications.

b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.

c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

d) All of Contec's packaging is compatible with hydrogen peroxide gassing applications.

e) These wipes are free of lint and loose fibers, and meet the definition of lint-free/low linting wipes according to the United States Pharmacopoeia Chapter 797 (USP-NF General Chapter <797> Pharmaceutical Compounding -Sterile Preparations) and the Institute of Environmental Sciences and Technology Recommended Practice IEST-RP-CC004.4

Test Methods:

1. CTM = Contec Test Method

2. IEST-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of environmental Sciences and Technology, Rolling Meadows IL.

PDSW075 | 101122

Copyright © 2022 Contec, Inc. All rights reserved.

Contact us: info@contecinc.com contecinc.com Contec, Inc. Spartanburg, SC 29303 USA tel: +1-864-503-8333

